

IKO hybritech Detail

Description:

IKO hybritech Detail is a isocyanatefree, solventfree and odourfree single-component coating based on flexible hybrid polymers.

IKO hybritech Detail cures through reaction with the air humidity.

Use:

IKO hybritech Detail is used to realise a waterproof connection to complex roof details, like flashings, domes, roof lights, chimneys, airconditioning nozzles, gutters etc.

Thanks to its high viscosity, IKO hybritech Detail doesn't flow down when applied on high flashings.

Colour:

Standard dusty grey (RAL 7037)

Packaging:

IKO hybritech Detail: 10kg metal tin (item number 02415110)

Storage:

6 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

Once opened, use the product within 1 month. A skin will form on top of the product that needs to be cut out and can't be mixed to the liquid product.

Certificates:

Production ISO 9001 & 14001



Technical characteristics:

| | |
|------------------|---|
| Dry substance | > 98% |
| Density | +/- 1,35 g/cm ³ |
| Viscosity | +/- 30.000 cPs (25°C, spindle 7, sp 10) |
| Hardness | +/- 80 (Shore A 23°C) |
| Tensile strength | +/- 5 N/mm ² |
| Elongation | +/- 120% |

Application:

| | |
|-----------------------|------------|
| Air temperature | 5°C - 35°C |
| Substrate temperature | 5°C - 30°C |
| Product temperature | 5°C - 30°C |

Consumption rate:

Min 2,5 kg/m²

Cleaning of tools:

IKO tech Cleaner

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from www.ikoflexia.com.